

PRODUCT DESCRIPTION

MavCoat Epoxy Primer HS is a 100% solids, zero VOC, blush resistant, and low viscosity epoxy primer that delivers excellent surface wetting, penetration, and extended open time to help seal concrete pores and promote adhesion. This easy-to-apply primer is ideal for use with other Maverick coatings, including **Decorative Chip** and **Metallic Additive** systems.

FEATURES & BENEFITS

- 100% solids
- Easy to apply
- Low viscosity
- Zero VOC
- Excellent adhesion
- Seals porous concrete
- Reduces pinholes, fish eyes, craters, and outgassing.

RECOMMENDED USES

- Use as a thin primer under all Maverick epoxy basecoats.

PRODUCT INFORMATION

| PRODUCT NAME | SIZE | COLOR/FINISH | ITEM NUMBER |
|--|----------------|---------------|-------------|
| MavCoat Epoxy Primer HS 100% Solids Epoxy Primer | 1.5-Gallon Kit | Clear / Gloss | 40008895 |

1.5 gallons *MavCoat Epoxy Primer HS* clear can be pigmented with 1 pint *Maverick MavTint* in colors including: Haze Gray, Light Gray, Deck Gray, Sandstone, White, Black, & Tile Red.

TECHNICAL DATA

| PHYSICAL DATA | |
|-----------------------|--------------------------------------|
| Components | 2 (Base & Activator) |
| Color | Clear |
| Finish | High Gloss |
| Mix Ratio (by volume) | 2 Base: 1 Activator |
| Curing Mechanism | Chemical reaction between components |
| Solids by Volume | 100% |
| Solids by Weight | 100% |
| Mixed Viscosity | 700 cP |
| VOC (EPA Method 24) | 0 g/L |
| Work Time | 30 - 35 minutes (@73°F, 45% RH) * |

*Higher temperatures will shorten pot-life and working time.

| THEORETICAL COVERAGE | | |
|---|----------------|-----------------|
| Wet Mills (microns) | 3 (76) - min. | 8 (203) - max. |
| Coverage sq. ft./gal. (m ² /L) | 200 (5) - min. | 533 (13) - max. |

| CURE TIMES | |
|--------------------|--------------------|
| Drying Schedule | 72°F (25°C) 50% RH |
| Tack Free | 10 hours |
| Light Foot Traffic | 24 hours |
| Heavy Traffic | 48 hours |
| Full Cure | 5 days |
| Minimum Recoat | 6 hours |
| Maximum Recoat | 24 hours ** |

**Apply a second coat of primer or the basecoat within 24 hours of the initial coat of *MavCoat Epoxy Primer HS*. If the re-coat window is missed, the coating system will need to be sanded.

PRODUCT INFORMATION

| PHYSICAL PROPERTIES | TEST METHOD | RESULTS |
|------------------------------|-------------|-----------------------------------|
| Adhesion | ASTM D4541 | > 400 psi (100% Concrete Failure) |
| Compressive Strength | ASTM D695 | 9,000 psi |
| Flammability | – | Self-extinguishing over concrete |
| Flexural Strength | ASTM D790 | 6,000 psi |
| Gloss @ 60° Angle | ASTM D523 | > 90 |
| Hardness, Shore D (24 hours) | ASTM D2240 | 75 |
| Tensile Strength | ASTM D638 | 3,000 psi |

SURFACE PREPARATION

Concrete and coated concrete surfaces must be sound, clean, dry and free of contaminants such as dirt, dust, grease, oil, silicones and other contaminants that may negatively affect adhesion.

MOISTURE VAPOR BARRIER:

A suitable moisture barrier must be in place for concrete slabs on-grade. If a moisture barrier is not in place, seasonal variations in ground moisture can cause excessive moisture vapor transmission (MVT) regardless of results measured prior to coating application. MVT rate must not exceed three pounds per 1,000 square feet per 24 hours, as directed by ASTM F1869. The relative humidity (RH) of the slab must not exceed 75%, as directed by ASTM F2170. If there is a moisture situation in excess of the above rate, the use of Maverick MVB Moisture Vapor Barrier Primer may be required. Consult a Maverick Representative for details and application procedures.

NEW/BARE CONCRETE:

Diamond grind or shotblast to a CSP 3 or greater surface profile, depending on total thickness of system. Refer to SSPC-SP13/NACE 6 or ICRI Technical Guideline No. 310.2.

New concrete must be cured a minimum of 28 days and should meet moisture vapor transmission (MVT) and relative humidity (RH) thresholds as described in Surface Preparation section.

PREVIOUSLY COATED SURFACES:

Clean surface to prevent any contaminants from being spread/redistributed to a greater area being prepared. Thoroughly grind the surface with 30 grit metal diamonds to completely remove any grout or topcoats that are not epoxy based and provide proper surface profile required for adhesion of the system.

SAFETY AND TECHNICAL

Refer to the SDS sheet before use. Safety precautions must be strictly followed during storage, handling, and use. Personal Protective Equipment (PPE) should be worn at all times. PPE will include (but is not limited to): Safety glasses with side shields and high-quality nitrile gloves. To acquire additional information or technical and safety data, please visit: mavtechsol.com.

APPLICATION EQUIPMENT

Assemble all equipment. Equipment will include (but is not limited to):

- Drill and Jiffy® type mixing blade
- Spiked Shoes
- Flat metal spring blade or flat EPDM squeegee.
- 3/8" shed-resistant woven roller covers with phenolic core.
- Edge rollers, chip brushes
- Painter's tape, duct tape, measuring and mixing containers

TEMPERATURE

| | | |
|----------|------------|------------|
| Air | 60° – 85°F | 16° – 29°C |
| Surface | 60° – 85°F | 16° – 29°C |
| Material | 60° – 85°F | 16° – 29°C |

Higher temperatures will shorten pot-life and working time.
Floor temperature must be at least 5 degrees over the current dew point.



MAVERICK
PERFORMANCE SOLUTIONS

MAVCOAT EPOXY PRIMER HS

APPLICATION PROCEDURE

MavCoat Epoxy Primer HS mix ratio is 2 Parts Base to 1 Part Activator by volume.

1. Pre-mix Base at low speed for 1 minute. Pour base into a 2–5 gallon mixing pail. If pigmenting, mix MavTint into the Base. Then, add Activator and mix for three minutes until uniform. Do not mix more material than can be applied in 10 – 15 minutes (material will stiffen or tack-up).
2. Immediately pour all mixed **MavCoat Epoxy Primer HS** on the floor in a long bead approximately 8 – 12 inches wide. Do not attempt to roll material out of a bucket or roller pan.
3. Wearing spiked shoes, spread evenly at 3 – 8 mils by pushing a flat squeegee or metal spring blade along the bead. Overlap previous passes in order to ensure concrete pinholes are filled. A tight, thin coat of primer with no backroll is the best way to minimize outgassing bubbles.
4. If back-rolling, use a non-shed 3/8" roller and back-roll the primer evenly across the squeegee passes to minimize application lines and leave a consistent film thickness.
5. After the **MavCoat Epoxy Primer HS** has set, inspect the surface for evidence that the substrate is not sealed. If pinholes are not completely sealed, outgassing may occur. If necessary apply an additional coat within 24 hours to ensure uniform coverage before applying the basecoat.

CLEAN UP & DISPOSAL

Clean up mixing and application equipment immediately after use. Use toluene, acetone or xylene; do not use alcohol. Follow solvent manufacturer's safety instructions. Be sure to follow all local, state and federal regulations when disposing of materials.

MAINTENANCE

To maintain the appearance and extend the life of the newly sealed surface, it is imperative to have a routine maintenance program. Dirt and debris that is tracked over a finished floor will quickly scratch and dull the surface. Place walk-off mats at entrances. Sweep and mop/scrub floors regularly using soft bristles/pads and a mild cleaner. Some cleaning products and equipment or improper use of these can damage a surface. Remove spills quickly to minimize damage and/or stains. For systems that support parked vehicles or other heavy items on rubber wheels, place a small piece of nonporous material, such as sheet metal or plexiglass between the tires and floor to prevent tire marks. Reapplication may be necessary in heavy traffic areas.

LIMITATIONS

- ⚠ Do not apply at a temperature or thickness not recommended.
- ⚠ Do not delay in pouring mixed material onto the floor.
- ⚠ Do not apply over loose or unsound concrete, asphalt or bitumen substrates, glazed tile or nonporous brick and tile, magnesite, copper, metal, polyesters, or elastomeric membranes.
- ⚠ Moving joints and shrinkage cracks may reflect through system. Joints that are designed to move may reflect through the finished flooring system if the are not honored.
- ⚠ Tire marking may occur.

SHELF LIFE AND STORAGE

24 months from date of manufacture when stored indoors in the original unopened container at 60°F – 85°F (16°C – 29°C) in a dry location with humidity below 65%.

- ⚠ Do not allow materials to freeze.

TECHNICAL ASSISTANCE



Information is available by calling Maverick
313-889-2526

LIMITED WARRANTY

Maverick warrants this product to be free from defect in the material that affects its performance for a period of one year (from date of purchase). Maverick will replace at no charge the quantity of the Coating that Maverick determines has failed to perform, as the sole and exclusive remedy for any breach of this warranty and/or any other defect or failure of the coating. Proof of purchase is required. Cost of labor for application of any product specifically is excluded. Warranty is void if Maverick products are mixed with or used in conjunction with materials that are substituted for Maverick products. Warranty is nontransferable.



MAVERICK
PERFORMANCE SOLUTIONS

CORPORATE OFFICE:

Maverick Performance Solutions
23460 Industrial Park Dr,
Farmington Hills, MI 48335
313-889-2526

PRODUCT DATA SHEET: 02/04/2026

Disclaimer: All information provided by Maverick, Inc. concerning Maverick products, including but not limited to, any recommendations and advice relating to the application and use of Maverick products, is given in good faith based on Maverick's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with Maverick's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual conditions and other factors outside of Maverick's control are such that Maverick assumes no liability for the provision of such information, advice, recommendations or instructions related to its products. The uses of Maverick product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s).

Maverick reserves the right to change the properties of its products without notice. All Maverick product(s) are subject to its current terms and conditions of sale which are available by calling (866) 515-8775.